

Universal Coatings, Inc.

Universal Coatings, Inc.
2430 Vantage Lane
Voice: 704-483-5885
Denver, NC 28037
Fax: 704-483-0195

July 12, 1989

INTERNATIONAL DISTRIBUTORS, INC.
Route 2 Box 2241
Mendenhall, MS 39114

Attention: Mr. Leslie Mallett

Ref: Lincoln Big-3 Industries

Dear Leslie,

I just wanted to let you know of a unique test we put Cerama-Seal through while visiting with a friend of mine at Lincoln Big-3 here in Baton Rouge. We submerged a sample of Cerama-Seal that had been brushed onto a piece of 3" x 8" x .035 aluminum of which half had been coated with brushed on Cerama-Seal to about a 20 mil coat. This product had cured for approximately 30 days. We submerged the sample in a bucket of liquid nitrogen which is 320 degrees below zero for approximately 2 minutes in order to give the sample adequate time to adjust temperature to the temperature of the liquid nitrogen. After removing the sample we could bend it with no cracking, separation, or visual effect to the product in any manner. We also noted that you could touch the Cerama-Seal without your finger sticking to it where you could not do this with the bare metal.

I know this is somewhat to the extremes but I thought it of interest as this proves again that Cerama-Seal is an outstanding product.

Sincerely yours,

Ted Crunkleton

J. Ted Crunkleton
President

Note: Cerama-Seal was the earlier
name for TEMP-COAT™